



# Wausau Coated Products, Inc.

## Facestock Specification UltraTherm<sup>®</sup> TC Direct Thermal

### **FACESTOCK DESCRIPTION: ULTRATHERM<sup>®</sup> TC DIRECT THERMAL**

Super smooth direct thermal paper fully top-coated for resistance to plasticizers, moisture, blood, oil, and fats. Abrasion resistant for excellent image retention. Medium speed sensitivity for standard speed thermal printers. Perfect facestock for industrial label applications, food packaging, and retail catchweight equipment.

Basis Weight (25 x 38 / 500) lbs.	54.9
Caliper, mils	3.1
Brightness, %	>89
Smoothness (Bekk)	>800
Stiffness, Gurley,mg, MD / CD	70 / 50
Tear, g, MD / CD	43 / 54
Heat Resistance	176°F
Maximum Density Temperature	118°F
Effective Activation Temperature	200°F
Regulatory Compliances	ASTM F963-08 Toy Safety, and CONEG

*All product specifications are for informational use only. Each customer and/or end user should determine the suitability of any product for their particular application. The above specifications are based on typical values and most current information. Specific products listed were current at the time of publication, however, all raw materials are subject to change.*

Shelf Life: One year when stored at 72°F / 50% RH.

August 2010