



Wausau Coated Products, Inc.

Product Specification W007669

60# Semi Gloss Optimized for HP Indigo Presses / R-201 / 40# SC

FACESTOCK DESCRIPTION: 60# SEMI GLOSS OPTIMIZED FOR HP INDIGO PRESSES

High quality, high brightness, highly opaque, semi gloss facestock with excellent gloss level. Top coated and optimized for HP Indigo Presses. Base sheet contains archival properties, is elemental chlorine free and lignin free. It features excellent ink anchorage and high strength for die cutting and matrix stripping.

Basis Weight (25 x 38 / 500) lbs.	60
Caliper, mils	3.0
GSM	88.8
Brightness, %	90
Opacity, %	91
Gloss	71
Smoothness, PPS, F/W	0.79/0.72
Tear, g, MD / CD	30 / 30
Tensile, lbs., MD / CD	35 / 17
pH	Alkaline
Regulatory Compliances	ASTM F963-96a Toy Safety, California Proposition 65, CONEG, and RoHS

ADHESIVE DESCRIPTION: R-201

An aggressive emulsion acrylic removable with good initial tack and moderate adhesion on most substrates. It has repositionability on some substrates for up to 24 hours. On some smooth surfaces, R-201 may grow to semi-permanency. As always, pretesting is recommended to determine suitability for a particular end-use application.

Type	Removable
Classification	Emulsion Acrylic
pH	Alkaline
Minimum Application Temp.	+40°F
Service Temperature Range	0°F to +175°F
Regulatory Compliances	Indirect Food 21 CFR 175.105 and RoHS

LINER DESCRIPTION: 40# SC

A supercalendered bleached kraft liner. Superior die-cutting and stripping properties. Recommended for roll-to-roll applications. Good back printability.

Basis Weight (25 x 38 / 500) lbs.	44.7
Caliper, mils	2.5
Brightness, %	78
Opacity, %	65
Tensile, lbs., MD / CD	34 / 22
Tear, g, MD / CD	32 / 34
Gloss, 75°	48
Regulatory Compliances	Indirect Food 21 CFR 176.170, and RoHS

All product specifications are for informational use only. Each customer and/or end user should determine the suitability of any product for their particular application. The above specifications are based on typical values and most current information. Specific products listed were current at the time of publication, however all raw materials are subject to change.

Shelf Life: Once year when stored at 72°F / 50% RH.

October 2010