



Wausau Coated Products, Inc.

Product Specification #W009470

60# Semi Gloss / P-842 / 40#

FACESTOCK DESCRIPTION: 60# SEMI GLOSS

Bright blue-white facestock with a medium gloss level. Has good opacity, brightness, and a smooth finish suitable for water-based and UV flexographic, UV letterpress, and offset printing applications

Basis Weight (25 x 38 / 500) lbs.	60
Caliper, mils	3.0
Tensile, lbs., MD / CD	35 / 17*
Tear, g, MD / CD	30 / 30
Brightness, %	90
Opacity, %	91
Smoothness, PPS, F/W	0.79/0.72*
Gloss	71
pH	Alkaline
Regulatory Compliances	FDA 21 CFR 175.105 for indirect food contact, CONEG, Heavy Metals, ASTM F963-96a Child Toy Safety, RoHS compliant, CA - AB 1108 Compliant, CA - Proposition 65, elemental chlorine free, non-ozone depleting and lignin free.

*Based on typical run data.

ADHESIVE DESCRIPTION: P-842

A highly aggressive rubber based permanent adhesive with superior adhesion to films, even in the presence of moisture. Excellent adhesion to corrugated, HDPE (high density polyethylene) and LDPE (low density polyethylene) surfaces, as well as polypropylene surfaces. It offers superior die-cutting and converting properties. Pretesting is recommended to determine end-use applicability. Excellent adhesive choice for dairy label applications.

Type	General Purpose Permanent
Classification	Rubber Based
Minimum Application Temp.	0°F
Service Temperature Range	-40°F to +160°F

LINER DESCRIPTION: 40# SC LINER

A supercalendered bleached kraft liner. Superior die-cutting and stripping properties. Recommended for roll-to-roll applications. Good back printability.

Basis Weight (25 x 38 / 500) lbs.	44.8
Caliper, mils	2.5
Brightness, %	81
Opacity, %	65
Tensile, lbs./in., MD / CD	34 / 22
Tear, G, MD / CD	32 / 34
Gloss, 75°	45
Regulatory Compliances	FDA 21 CFR 175.105 for incidental food contact, California Clean Water (Prop. 65), and NAFTA. Lignin free.

All product specifications are for informational use only. Each customer and/or end user should determine the suitability of any product for their particular application. The above specifications are based on typical values and most current information.

Shelf Life: One year when stored at 72°F / 50% RH.

08J