



Wausau Coated Products, Inc.

Product Specification #W009476

60# Semi Gloss / F-590 / 40#

FACESTOCK DESCRIPTION: 60# SEMI GLOSS

Bright blue-white facestock with a medium gloss level. Has good opacity, brightness, and a smooth finish suitable for water-based and UV flexographic, UV letterpress, and offset printing applications

Basis Weight (25 x 38 / 500) lbs.	60
Caliper, mils	3.0
Tensile, lbs., MD / CD	35 / 17*
Tear, g, MD / CD	30 / 30
Brightness, %	90
Opacity, %	91
Smoothness, PPS, F/W	0.79/0.72*
Gloss	71
pH	Alkaline
Regulatory Compliances	FDA 21 CFR 175.105 for indirect food contact, CONEG, Heavy Metals, ASTM F963-96a Child Toy Safety, RoHS compliant, CA - AB 1108 Compliant, CA - Propisition 65, elemental chlorine free, non-ozone depleting and lignin free.

*Based on typical run data.

ADHESIVE DESCRIPTION: F-590

A very aggressive rubber based freezer permanent adhesive exhibiting high initial tack and very good adhesion to a wide variety of packaging materials and films. F-590 will adhere to a frosty surface depending upon the substrate and the amount of frost and/or free moisture present. Pretesting is recommended to determine end-use applicability.

Type	Freezer Permanent
Classification	Rubber Based
Regulatory Compliances	FDA 21 CFR 175.105 for incidental food contact, CONEG, ASTM F963a Child Toy Safety, and NAFTA.
Minimum Application Temp.	-15°F
Service Temperature Range	-40°F to +130°F

LINER DESCRIPTION: 40# SC LINER

A supercalendered bleached kraft liner. Superior die-cutting and stripping properties. Recommended for roll-to-roll applications. Good back printability.

Basis Weight (25 x 38 / 500) lbs.	44.8
Caliper, mils	2.5
Brightness, %	81
Opacity, %	65
Tensile, lbs./in., MD / CD	34 / 22
Tear, G, MD / CD	32 / 34
Gloss, 75°	45
Regulatory Compliances	FDA 21 CFR 175.105 for incidental food contact, California Clean Water (Prop. 65), and NAFTA. Lignin free.

All product specifications are for informational use only. Each customer and/or end user should determine the suitability of any product for their particular application. The above specifications are based on typical values and most current information.

Shelf Life: One year when stored at 72°F / 50% RH.

08J