



Wausau Coated Products, Inc.

Product Specification W012061

60# Semi Gloss with 10% PCW / PCT-950 / 80# FSC

FACESTOCK DESCRIPTION: 60# SEMI GLOSS WITH 10% PCW

Bright white facestock with a medium gloss level featuring 10% post consumer waste. Has high opacity and a smooth finish suitable for water-based and UV flexographic, UV letterpress, and offset printing applications. This premium printing paper is FSC certified and elemental chlorine free (EFC).



Basis Weight (25 x 38 / 500) lbs.	60
Caliper, mils	2.85
Brightness, %	92
Opacity, %	91
Gloss	72
Smoothness, PPS	1.0-1.1
Tear, g, MD / CD	31 / 35
Tensile, lbs., MD / CD	27 / 15
pH	Alkaline
Recycled Content, %	10
PCW, %	10
Regulatory Compliances	FDA 21 CFR 176.170 for indirect food contact, CONEG, Heavy Metals, ASTM F963-96a Child Toy Safety, Federal Hazardous Substances Act 16 CFR, Part 1500.3 Acute Oral Toxicity, Part 1500.42 Primary Eye Irritant, Part 1500.41 Primary Skin Irritant legislation, RoHS, Non-ozone depleting, lignin free, elemental chlorine free & FSC certified

ADHESIVE DESCRIPTION: PCT-950

A cold temperature emulsion acrylic permanent which exhibits good initial tack and good adhesion to a variety of substrates. Adhesion to rigid plastics, films, glass, and painted metals is good. Cuts and die-cuts cleanly. Good choice for sheet and roll-to-sheet applications.

Type	Cold Temperature Permanent
Classification	Emulsion Acrylic
pH	Alkaline
Minimum Application Temp.	+35°F
Service Temperature Range	-10°F to +200°F
Regulatory Compliances	FDA 21 CFR 175.105 for incidental food contact, CONEG, Heavy Metals, ASTM F963A Child Toy Safety, Acute Oral Toxicity, Primary Dermal Irritant, Primary Eye Irritant, and NAFTA

LINER DESCRIPTION: 80# LINER WITH 10% PCW

Dimensionally stable clay-coated bleached kraft liner designed for roll-to-sheet applications.

Basis Weight (25 x 38/500) lbs.	80
Caliper, mils	4.4
Brightness, %	92
Opacity, %	95
Gloss, 75°	26
Regulatory Compliances	FSC Certified, Elemental Chlorine Free



All product specifications are for informational use only. Each customer and/or end user should determine the suitability of any product for their particular application. The above specifications are based on typical values and most current information. Specific products listed were current at the time of publication, however, all raw materials are subject to change.

Shelf Life: One year when stored at 72°F / 50% RH.

February 2009