



Wausau Coated Products, Inc.

Product Specification W013201

60# High Gloss Optimized for HP Indigo Presses / PCT-245 / 40# SC

FACESTOCK DESCRIPTION: 60# HIGH GLOSS OPTIMIZED FOR HP INDIGO PRESSES

A premium quality high gloss with a blue-white shade and mirror-smooth surface. It has a consistent finish that provides excellent ink receptivity and maximum toner anchorage. Top coated surface that is optimized for HP Indigo Presses.

Basis Weight (25 x 38 / 500) lbs.	59.5
Caliper, mils	3.6
GSM	88
Tensile, lbs., MD / CD	39 / 18
Tear, g, MD / CD	41 / 42
Brightness, %	83* (*Typical Run Value)
Opacity, %	93
pH	Slightly Acidic
Regulatory Compliances	Indirect Food 21 CFR 176.170

ADHESIVE DESCRIPTION: PCT-245

A cold temperature emulsion acrylic permanent which exhibits good initial tack and good adhesion to a variety of substrates including corrugated, rigid plastics, films, glass, and painted metal surfaces. It offers excellent die-cutting and stripping characteristics. Designed for face and back label use and remains affixed when immersed in an ice bucket. It also features short term repositionability on bottles.

Type	Cold Temperature Permanent
Classification	Emulsion Acrylic
pH	Alkaline
Minimum Application Temp.	+25°F
Service Temperature Range	-10°F to +200°F
Regulatory Compliances	FDA 21 CFR 175.105 for incidental food contact, CONEG, Heavy Metals, ASTM 963a Child Toy Safety, Acute Oral Toxicity, Primary Dermal Irritant, Primary Eye Irritant, and NAFTA.

LINER DESCRIPTION: 40# SC LINER

A supercalendered bleached kraft liner. Superior die-cutting and stripping properties. Recommended for roll-to-roll applications. Good back printability.

Basis Weight (25 x 38 / 500) lbs.	44.7
Caliper, mils	2.5
Brightness, %	78
Opacity, %	65
Tensile, lbs./in., MD / CD	34 / 22
Tear, G, MD / CD	32 / 34
Gloss, 75°	48
Regulatory Compliances	FDA 21 CFR 176.170 for incidental food contact, California Clean Water/Proposition 65, NAFTA, and lignin free.

All product specifications are for informational use only. Each customer and/or end user should determine the suitability of any product for their particular application. The above specifications are based on typical values and most current information. Specific products listed were current at the time of publication, however, all raw materials are subject to change.

Shelf Life: One year when stored at 72°F / 50% RH.

February 2009