

FACESTOCK DESCRIPTION: 55# SEMI GLOSS OPTIMIZED FOR HP INDIGO PRESSES

A bright white Semi Gloss facestock with good opacity and medium gloss level. Top coated and optimized for HP Indigo Presses. It has FSC®, SFI, and PEFC certifications. It features excellent ink anchorage and high strength for die cutting and matrix stripping.



The mark of responsible forestry

Basis Weight (25 x 38 / 500) lbs.	55
Caliper, mils	3.2
Brightness, %	87
Opacity, %	89
Gloss, %	62
Tear, g, MD	55
Tensile, lbs, CD	17
Regulatory Compliance	ASTM F963-08 Toy Safety, California Proposition 65, CONEG, RoHS, REACH, SFI, PEFC & FSC certified

FSC® is a registered trademark of Forest Stewardship Council™

ADHESIVE DESCRIPTION: PCT-245

A cold temperature emulsion acrylic permanent which exhibits good initial tack and good adhesion to a variety of substrates including corrugated, rigid plastics, films, glass, and painted metal surfaces. It offers excellent die-cutting and stripping characteristics. Designed for face and back label use and remains affixed when immersed in an ice bucket. It also features short term repositionability on bottles.

Type	Cold Temperature Permanent
Classification	Emulsion Acrylic
pH	Alkaline
Minimum Application Temp.	+25°F
Service Temperature Range	-10°F to +200°F
Regulatory Compliances	Acute Oral Toxicity 16 CFR 1500.3, Primary Skin Irritant 16 CFR 1500.41, Primary Eye Irritant 16 CFR 1500.42, Indirect Food 21 CFR 175.105, ASTM F963-96a Toy Safety, CONEG, RoHS, & REACH

LINER DESCRIPTION: 40# SC LINER

A supercalendered bleached kraft liner. Superior die-cutting and stripping properties. Recommended for roll-to-roll applications. Good back printability.

Basis Weight (25 x 38 / 500) lbs.	44.7
Caliper, mils	2.5
Brightness, %	78
Opacity, %	65
Tensile, lbs., MD / CD	34 / 22
Tear, g, MD / CD	32 / 34
Gloss, 75°	48
Regulatory Compliances	FDA 21 CFR 176.170 for incidental food contact, RoHS, and NAFTA

All product specifications are for informational use only. Each customer and/or end user should determine the suitability of any product for their particular application. The above specifications are based on typical values and most current information. Specific products listed were current at the time of publication, however, all raw materials are subject to change.

Shelf Life: One year when stored at 72°F / 50% RH.

June 2011