



# Wausau Coated Products, Inc.

Product Specification WC0303

60# Semi Gloss / Removable / 80# Score Back

Sheet Size 17-1/4" x 22-1/4"

### **FACESTOCK DESCRIPTION: 60# Semi Gloss**

High quality facestock with a smooth surface and a medium gloss level. Features excellent runnability and color reproduction. Has good opacity and high brightness, and is suitable for water-based and UV flexographic, UV letterpress, and offset printing applications. Contains archival properties...elemental chlorine free, non-ozone depleting and lignin free with an alkaline pH level.

Basis Weight (25 x 38 / 500), lbs.	60
Caliper, mils	3
Brightness, %	90
Gloss, 75°, %	71
Opacity, %	91
Tear, MD / CD, g	30 / 30
Tensile, MD / CD, lbs.	35 / 17
Smoothness, PPS, F/W, units	0.79/0.72
pH	Alkaline
Regulatory Compliances	ASTM F963 Child Toy Safety, California Proposition 65, CONEG, Lignin Free, RoHS, REACH, CPSIA, Non-ozone Depleting, Elemental Chlorine Free

### **ADHESIVE DESCRIPTION: Removable**

An aggressive emulsion acrylic removable with good initial tack and moderate adhesion on most substrates. It is also repositionable on most substrates for up to 24 hours. On some smooth surfaces, this adhesive may grow to semi-permanency. As always, pretesting is recommended to determine suitability for a particular end-use application.

Type	Removable
Classification	Emulsion Acrylic
pH	Alkaline
Minimum Application Temp., °F	40
Service Temperature Range, °F	0 to +175
Regulatory Compliances	ASTM F963 Child Toy Safety, CONEG, RoHS, Non-ozone Depleting, FDA 21 CFR 175.105, Primary Skin Irritant 16 CFR 1500.41

### **LINER DESCRIPTION: 80# Score Back**

Clay-coated bleached kraft liner designed for roll-to-sheet applications. Manufactured with liner scores every 1-1/4" apart.

Basis Weight (25 x 38 / 500), lbs.	80
Caliper, mils	4.6
Brightness, %	78
Gloss, 75°, %	25
Opacity, %	84
Tear, MD / CD, g	70 x 70
Tensile, MD / CD, n/in	220 / 100
Regulatory Compliances	ASTM F963 Child Toy Safety, CONEG, RoHS, REACH, FDA 21 CFR 175.105

All product specifications are for informational use only. Each customer and/or end user should determine the suitability of any product for their particular application. The above specifications are based on typical values and most current information. Specific products listed were current at the time of publication, however, all raw materials are subject to change.

Shelf Life: One year when stored at 72°F / 50% RH.