



FACESTOCK DESCRIPTION: 60# Uncoated Offset

Premium quality uncoated paper with high brightness and an extremely smooth surface. Features high strength, high opacity, and has an absorbent surface. It is laser, inkjet, and digital copier compatible as well as acid-free, lignin-free and ECF.

| | |
|------------------------------------|--|
| Basis Weight (25 x 38 / 500), lbs. | 57 |
| Caliper, mils | 4 |
| Brightness, % | 95 |
| Opacity, % | 95 |
| Tear, MD / CD, g | 70 / 60 |
| Tensile, MD / CD, lbs. | 23 / 17 |
| pH | Acid Free |
| Regulatory Compliances | Elemental Chlorine Free, Non-ozone Depleting, CPSIA, REACH, RoHS, CONEG, California Proposition 65, ASTM F963 Child Toy Safety, Acid Free, Lignin Free |

ADHESIVE DESCRIPTION: Permanent

A cold temperature emulsion acrylic permanent which exhibits good initial tack and good adhesion to a variety of substrates. Adhesion to rigid plastics, films, glass, and painted metals is good. Cuts and die-cuts cleanly. Good choice for sheet and roll-to-sheet applications.

| | |
|-------------------------------|--|
| Type | Cold Temperature Permanent |
| Classification | Emulsion Acrylic |
| pH | Alkaline |
| Minimum Application Temp., °F | 35 |
| Service Temperature Range, °F | -10 to +200 |
| Regulatory Compliances | CONEG, RoHS, Acute Oral Toxicity 16 CFR 1500.3, REACH, FDA 21 CFR 175.105, Primary Skin Irritant 16 CFR 1500.41, Primary Eye Irritant 16 CFR 1500.42 |

LINER DESCRIPTION: 80# Zero Split

Clay-coated bleached kraft liner designed for roll-to-sheet applications.

| | |
|------------------------------------|--|
| Basis Weight (25 x 38 / 500), lbs. | 80 |
| Caliper, mils | 4.6 |
| Brightness, % | 78 |
| Gloss, 75°, % | 25 |
| Opacity, % | 84 |
| Tear, MD / CD, g | 70 x 70 |
| Tensile, MD / CD, n/in | 220 / 100 |
| Regulatory Compliances | ASTM F963 Child Toy Safety, CONEG, RoHS, REACH, FDA 21 CFR 175.105 |

All product specifications are for informational use only. Each customer and/or end user should determine the suitability of any product for their particular application. The above specifications are based on typical values and most current information. Specific products listed were current at the time of publication, however, all raw materials are subject to change.

Shelf Life: One year when stored at 72°F / 50% RH.