



Wausau Coated Products, Inc.

Product Specification WC0405

60# High Gloss / Removable / 80# Zero Split

Sheet Size 17-1/4" x 22-1/4"

FACESTOCK DESCRIPTION: 60# High Gloss

A premium quality high gloss with a blue-white shade and mirror-smooth surface. It has a consistent finish that provides excellent ink receptivity and maximum toner anchorage. Suitable for letterpress, offset, gravure, and water and UV flexographic printing applications.

Basis Weight (25 x 38 / 500), lbs.	57.4
Caliper, mils	3.7
Brightness, %	87
Gloss, 75°, %	90
Opacity, %	90
Tear, MD / CD, g	40 / 35
Tensile, MD / CD, lbs.	25 / 12
Regulatory Compliances	California Proposition 65, CONEG, RoHS, FDA 21 CFR 176.170, REACH, CPSIA

NULL

ADHESIVE DESCRIPTION: Removable

An aggressive emulsion acrylic removable with good initial tack and moderate adhesion on most substrates. It is also repositionable on most substrates for up to 24 hours. On some smooth surfaces, this adhesive may grow to semi-permanency. As always, pretesting is recommended to determine suitability for a particular end-use application.

Type	Removable
Classification	Emulsion Acrylic
pH	Alkaline
Minimum Application Temp., °F	40
Service Temperature Range, °F	0 to +175
Regulatory Compliances	ASTM F963 Child Toy Safety, CONEG, RoHS, Non-ozone Depleting, FDA 21 CFR 175.105, Primary Skin Irritant 16 CFR 1500.41

LINER DESCRIPTION: 80# Zero Split

Clay-coated bleached kraft liner designed for roll-to-sheet applications.

Basis Weight (25 x 38 / 500), lbs.	80
Caliper, mils	4.6
Brightness, %	78
Gloss, 75°, %	25
Opacity, %	84
Tear, MD / CD, g	70 x 70
Tensile, MD / CD, n/in	220 / 100
Regulatory Compliances	ASTM F963 Child Toy Safety, CONEG, RoHS, REACH, FDA 21 CFR 175.105

All product specifications are for informational use only. Each customer and/or end user should determine the suitability of any product for their particular application. The above specifications are based on typical values and most current information. Specific products listed were current at the time of publication, however, all raw materials are subject to change.

Shelf Life: One year when stored at 72°F / 50% RH.