

FACESTOCK DESCRIPTION: 55# Brown Kraft

Brown Kraft has the coloring and consistency of a brown paper grocery bag and is designed to work through both inkjet and laser printers. Brown kraft gives a cozy, primitive, rustic, or "earthy" look for label applications. Perfect for candle labeling, art, crafts, gourmet foods, or on any label requiring a unique appearance.

| | |
|------------------------------------|---------|
| Basis Weight (25 x 38 / 500), lbs. | 55 |
| Caliper, mils | 6 |
| Tear, MD / CD, g | 86 / 91 |
| Tensile, MD / CD, lbs. | 41 / 21 |

ADHESIVE DESCRIPTION: PCT-6950

A cold temperature emulsion acrylic permanent which exhibits good initial tack and good adhesion to a variety of substrates. Adhesion to rigid plastics, films, glass, and painted metals is good. Cuts and die-cuts cleanly. Good choice for sheet and roll-to-sheet applications.

| | |
|-------------------------------|--|
| Type | Cold Temperature Permanent |
| Classification | Emulsion Acrylic |
| pH | Alkaline |
| Minimum Application Temp., °F | +3F |
| Service Temperature Range, °F | -10 to +200 |
| Regulatory Compliances | CONEG, RoHS, Acute Oral Toxicity 16 CFR 1500.3, REACH, FDA 21 CFR 175.105, Primary Skin Irritant 16 CFR 1500.41, Primary Eye Irritant 16 CFR 1500.42 |

LINER DESCRIPTION: 52# Laser

A supercalendered bleached kraft liner specially designed for sheeted applications and well suited for laser printing. Features excellent dimensional stability. Recommended for roll-to-sheet applications.

| | |
|------------------------------------|-----|
| Basis Weight (25 x 38 / 500), lbs. | 50 |
| Caliper, mils | 3.4 |
| Brightness, % | 80 |
| Opacity, % | 82 |
| Tear, CD, g | 52 |
| Tensile, MD, lbs. | 31 |

All product specifications are for informational use only. Each customer and/or end user should determine the suitability of any product for their particular application. The above specifications are based on typical values and most current information. Specific products listed were current at the time of publication, however, all raw materials are subject to change.

Shelf Life: One year when stored at 72°F / 50% RH.