



70# Bright Silver Foil Optimized for HP Indigo Presses / WL-100 / 44# PK

FACESTOCK DESCRIPTION: 70# Bright Silver Foil Optimized for HP Indigo Presses

Bright Silver foil laminated to a paper base stock. Top coated and optimized for HP Indigo Presses. Can also be foil stamped and embossed. Typical end uses include high quality packaging such cosmetics, gourmet foods, wines, and gift items.

Basis Weight (25 x 38 / 500), lbs.	70
Caliper, mils	3.6
Tear, MD / CD, g	50 / 51
Tensile, MD / CD, lbs.	36 / 23
pH	7 - 7.5

ADHESIVE DESCRIPTION: WL-100

A cold temperature emulsion acrylic permanent, with good initial tack and short term repositionability. WL100 is an excellent performer both at room temperature and in ice bucket conditions on a variety of substrates including glass, rigid plastic, films, metals, and corrugated. Designed for beverage labels, it provides good die-cutting and stripping characteristics.

Type	Cold Temperature Permanent
Classification	Emulsion Acrylic
pH	Alkaline
Minimum Application Temp., °F	25
Service Temperature Range, °F	-10 to +200
Regulatory Compliances	Natural Rubber Latex Free, CONEG, RoHS, Acute Oral Toxicity 16 CFR 1500.3, REACH, CPSIA, Non-ozone Depleting, FDA 21 CFR 175.105, Primary Skin Irritant 16 CFR 1500.41, Primary Eye Irritant 16 CFR 1500.42, ASTM F963 Child Toy Safety

LINER DESCRIPTION: 44# PK

A polylam brown kraft liner with superior die-cutting and stripping properties. Designed for high-speed label dispensing and is recommended for roll-to-roll applications.

Basis Weight (25 x 38 / 500), lbs	45.5# +/- 10%
Caliper, mils	3.3 +/- 10%
Regulatory Compliances	CONEG, RoHS, REACH

All product specifications are for informational use only. Each customer and/or end user should determine the suitability of any product for their particular application. The above specifications are based on typical values and most current information. Specific products listed were current at the time of publication, however, all raw materials are subject to change.

Shelf Life: Six months when stored at 60-75°F / 35-55% RH.