

**FACESTOCK DESCRIPTION: 2 Mil Clear Polypropylene**

A biaxially oriented, optically clear top coated polypropylene film with excellent clarity to produce a "no label" look when used with an appropriate adhesive. Features excellent hot/cold moisture resistance and performs well for semi-squeezable applications, but has high stiffness for good conversion and automatic dispensing. Top coated for excellent printability and is suitable for flexographic, thermal transfer, gravure, and letterpress printing applications. Please consult your ink supplier

Caliper, mils	2
Yield, sq. in/lb	15,000
Gloss, Gardner (45°), %	90
Tensile Strength, MD / TD, psi	21,000 / 38,000
Elongation at break, MD / TD, %	180 / 55
Dim. Stab. 60 sec at 248oF, MD / TD, %	4 / 2
Regulatory Compliances	ASTM F963 Child Toy Safety, California Proposition 65, CONEG, RoHS, REACH, Non-ozone Depleting, FDA 21 CFR 177.1520

ADHESIVE DESCRIPTION: i8017

i8017 is an ultra-aggressive permanent designed for difficult-to-label surfaces. It offers excellent initial tack and ultimate adhesion to a variety of substrates. i8017 is UV resistant, water resistant, and offers some solvent resistance.

Type	High Performance Acrylic
Classification	Acrylic
pH	Slightly Acidic
Minimum Application Temp., °F	20
Service Temperature Range, °F	-20 to +300
Regulatory Compliances	California Proposition 65, CONEG, Natural Rubber Latex Free, REACH, RoHS, FDA 21 CFR 175.105, FDA 21 CFR 175.125 Table 2 D-G, FDA 21 CFR 176.180

LINER DESCRIPTION: 40# SC

A supercalendered bleached liner. Superior die-cutting and stripping properties. Recommended for roll-to-roll applications. Good back printability.

Basis Weight (25 x 38 / 500), lbs.	42
Caliper, mils	2.5

All product specifications are for informational use only. Each customer and/or end user should determine the suitability of any product for their particular application . The above specifications are based on typical values and most current information. Specific products listed were current at the time of publication, however, all raw materials are subject to change.

Shelf Life: One year when stored at 72°F / 50% RH.