



Wausau Coated Products, Inc.

Product Specification DC01867

70# Bright Silver Foil / Permanent / 52# Laser

8-1/2" x 11" Sheet, 30-up, Label Size 2-5/8" x 1"

FACESTOCK DESCRIPTION: 70# Bright Silver Foil

Bright silver foil laminated to a paper base stock. Acrylic top coated for excellent ink receptivity. Special inks are required and testing is recommended. Can also be foil stamped and embossed. Typical end uses include high quality packaging such cosmetics, gourmet foods, wines, and gift items.

Basis Weight (25 x 38 / 500), lbs.	70
Caliper, mils	3.6
Tear, MD / CD, g	50 / 51
Tensile, MD / CD, lbs.	36 / 23
pH	7 - 7.5
Regulatory Compliances	ASTM F963 Child Toy Safety, California Proposition 65, CONEG, REACH, FDA 21 CFR 175.105

ADHESIVE DESCRIPTION: Permanent

A cold temperature emulsion acrylic permanent which exhibits good initial tack to a variety of substrates. Adhesion to rigid plastics, film, glass, and painted metals is good. Die-cuts cleanly. Designed for laser applications and is a good choice for roll-to-sheet applications.

Classification	Emulsion Acrylic
Service Temperature Range, °F	-10 to +200
Minimum Application Temp., °F	35
pH	Alkaline
Type	Cold Temperature Permanent
Regulatory Compliances	California Proposition 65, CONEG, RoHS, Acute Oral Toxicity 16 CFR 1500.3, REACH, FDA 21 CFR 175.105, Primary Skin Irritant 16 CFR 1500.41, Primary Eye Irritant 16 CFR 1500.42

LINER DESCRIPTION: 52# Laser

A supercalendered bleached kraft liner specially designed for sheeted applications and well suited for laser printing. Features excellent dimensional stability. Recommended for roll-to-sheet applications.

Basis Weight (25 x 38 / 500), lbs.	50
Caliper, mils	3.4
Brightness, %	80
Opacity, %	82
Tear, CD, g	52
Tensile, MD, lbs.	31

All product specifications are for informational use only. Each customer and/or end user should determine the suitability of any product for their particular application. The above specifications are based on typical values and most current information. Specific products listed were current at the time of publication, however, all raw materials are subject to change.

Shelf Life: One year when stored at 72°F / 50% RH.