



FACESTOCK DESCRIPTION: 2.6 Mil White Top Coated Polypropylene

A white polypropylene film top coated and suitable for Domino UV Inkjet Presses. It is very durable with high opacity and is biaxially oriented, cavitated, with good stiffness for conversion and automatic label dispensing.

Caliper, mils	2.7
Yield, sq. in/lb	14,300
Gloss, Gardner (45°), %	68
Opacity, %	88
Tensile Strength, MD / CD, psi	13,000 / 27,400
Elongation at Break, MD/CD, %	200 / 50
Stiffness, Gurley, MD / TD, mg	24 / 41
Dimensional Stability, MD / TD, %	-4.3 / -3.4

ADHESIVE DESCRIPTION: R-2150+

An excellent removable adhesive with low to moderate adhesion on most surfaces, R-2150+ is a good choice for a variety of removable applications. It functions most effectively on smooth surfaces, including glass, paper and painted metal. It has excellent stability and demonstrates very little growth in adhesion over time however, adhesion growth will vary depending upon substrate. Pretesting is recommended to determine end-use applicability.

Type	Ultra-Removable
Classification	Emulsion Acrylic
pH	Neutral to Slightly Alkaline
Minimum Application Temp., °F	-10
Service Temperature Range, °F	-40 to +160
Regulatory Compliances	ASTM F963 Child Toy Safety, CONEG, RoHS, Acute Oral Toxicity 16 CFR 1500.3, CPSIA, FDA 21 CFR 175.105, Primary Skin Irritant 16 CFR 1500.41, Primary Eye Irritant 16 CFR 1500.42

LINER DESCRIPTION: 40# SC

A supercalendered bleached liner. Superior die-cutting and stripping properties. Recommended for roll-to-roll applications. Good back printability.

Basis Weight (25 x 38 / 500), lbs.	44.7
Caliper, mils	2.5
Brightness, %	78
Gloss, 75°, %	48
Opacity, %	65
Tear, MD / CD, g	32 / 34
Tensile, MD / CD, lbs.	34 / 22
Regulatory Compliances	ASTM F963 Child Toy Safety, CONEG, RoHS, REACH

All product specifications are for informational use only. Each customer and/or end user should determine the suitability of any product for their particular application. The above specifications are based on typical values and most current information. Specific products listed were current at the time of publication, however, all raw materials are subject to change.

Shelf Life: One year when stored at 72°F / 50% RH.