



FACESTOCK DESCRIPTION: 3.4 Mil White UV Inkjet Flexible Vinyl

A smooth flexible vinyl film suitable for EFI Jetrion 4900 and Durst Tao UV Inkjet Presses. It has high durability and moisture resistance for outdoor label applications. It also has good chemical resistance.

| | |
|--------------------------------|--|
| Caliper, mils | 3.4 |
| Yield, sq. in/lb | 5,576 |
| Tensile Strength, MD / CD, psi | 3800 / 3350 |
| Brightness, % | 87.4 |
| Elongation Rate, MD / CD, % | 120 / 242 |
| Regulatory Compliances | ASTM F963 Child Toy Safety, California Proposition 65, CONEG, RoHS |

Avoid exposure to ozone, exhaust fumes or solvent vapors as the absorptive nature of the print receptive topcoat could result in discoloration.

ADHESIVE DESCRIPTION: SP-920

An aggressive general purpose emulsion acrylic adhesive with excellent initial tack and good adhesion to a variety of surfaces including corrugated and polyolefins. Designed with good die-cutting, stripping, and trimming properties.

| | |
|-------------------------------|--|
| Type | General Purpose Permanent |
| Classification | Emulsion Acrylic |
| pH | Alkaline |
| Minimum Application Temp., °F | 35 |
| Service Temperature Range, °F | -20 to +220 |
| Regulatory Compliances | CONEG, RoHS, Acute Oral Toxicity 16 CFR 1500.3, REACH, FDA 21 CFR 175.105, Primary Skin Irritant 16 CFR 1500.41, Primary Eye Irritant 16 CFR 1500.42 |

LINER DESCRIPTION: 40# SC

A supercalendered bleached liner. Superior die-cutting and stripping properties. Recommended for roll-to-roll applications. Good back printability.

| | |
|------------------------------------|-----|
| Basis Weight (25 x 38 / 500), lbs. | 42 |
| Caliper, mils | 2.5 |

All product specifications are for informational use only. Each customer and/or end user should determine the suitability of any product for their particular application. The above specifications are based on typical values and most current information. Specific products listed were current at the time of publication, however, all raw materials are subject to change.

Shelf Life: One year when stored at 72°F / 50% RH.