



Wausau Coated Products, Inc.

Product Specification DC02763

60# Semi Gloss Laser / Permanent / 52# Laser

8-1/2" x 11" Sheet, 14-up, Label Size 4" x 1-1/3"

FACESTOCK DESCRIPTION: 60# Semi Gloss Laser

High quality facestock with a smooth surface and a medium gloss level. Features excellent runnability and color reproduction. Has good opacity and high brightness, and is suitable for laser and offset printing applications. Contains archival properties...elemental chlorine free, non-ozone depleting and lignin free with an alkaline pH level.

Basis Weight (25 x 38 / 500), lbs	60
Caliper, mils	3.0
Brightness, %	90
Gloss, 75°, %	71
Opacity, %	91
Tear, MD / CD, g	30 / 30
Tensile, MD / CD, lbs	35 / 17
Smoothness, PPS, F/W, units	0.79/0.72
pH	Alkaline
Regulatory Compliances	REACH, RoHS, CONEG, California Proposition 65, ASTM F963 Child Toy Safety, FDA 21 CFR 176.170, Lignin Free, Non-ozone Depleting, Elemental Chlorine Free, FDA 21 CFR 176.180, CPSIA

ADHESIVE DESCRIPTION: Permanent

A cold temperature emulsion acrylic permanent which exhibits good initial tack to a variety of substrates. Adhesion to rigid plastics, film, glass, and painted metals is good. Die-cuts cleanly. Designed for laser applications and is a good choice for roll-to-sheet applications.

Service Temperature Range, °F	-10 to +200
Minimum Application Temp., °F	35
pH	Alkaline
Classification	Emulsion Acrylic
Type	Cold Temperature Permanent
Regulatory Compliances	California Proposition 65, CONEG, RoHS, Acute Oral Toxicity 16 CFR 1500.3, REACH, FDA 21 CFR 175.105, Primary Skin Irritant 16 CFR 1500.41, Primary Eye Irritant 16 CFR 1500.42

LINER DESCRIPTION: 52# Laser

A supercalendered bleached kraft liner specially designed for sheeted applications and well suited for laser printing. Features excellent dimensional stability. Recommended for roll-to-sheet applications.

Basis Weight (25 x 38 / 500), lbs.	50
Caliper, mils	3.4
Brightness, %	80
Opacity, %	82
Tear, CD, g	52
Tensile, MD, lbs.	31

All product specifications are for informational use only. Each customer and/or end user should determine the suitability of any product for their particular application. The above specifications are based on typical values and most current information. Specific products listed were current at the time of publication, however, all raw materials are subject to change.

Shelf Life: One year when stored at 72°F / 50% RH.