



Wausau Coated Products, Inc.

Product Specification W025346
63# Bright Silver Metalized Paper
for Xeikon Presses / PCT-245 / 44# PK

FACESTOCK DESCRIPTION: 63# Bright Silver Metalized Paper for Xeikon Presses

A smooth bright silver metalized paper with the appearance of foil. Has superior converting properties and is top coated for Xeikon Presses.

Basis Weight (25 x 38 / 500), lbs.	63
Caliper, mils	3.2
Tear, MD / CD, g	48 / 48
Tensile, MD / CD, lbs.	34 / 20
Stiffness, (Gurley), MD/ CD, mg	141 / 95
Regulatory Compliances	ASTM F963 Child Toy Safety, California Proposition 65, CONEG, CPSIA, Non-ozone Depleting

ADHESIVE DESCRIPTION: PCT-245

A cold temperature emulsion acrylic permanent which exhibits good initial tack and good adhesion to a variety of substrates including corrugated, rigid plastics, films, glass, and painted metal surfaces. It offers excellent die-cutting and stripping characteristics. Adhesive designed for face and back label use on glass bottles and remains affixed when immersed in an ice bucket. It also features short term repositionability on bottles and hot water removability depending on face, substrate, water

Type	Cold Temperature Permanent
Classification	Emulsion Acrylic
pH	Alkaline
Minimum Application Temp., °F	25
Service Temperature Range, °F	-10 to +200
Regulatory Compliances	ASTM F963 Child Toy Safety, CONEG, RoHS, Acute Oral Toxicity 16 CFR 1500.3, REACH, FDA 21 CFR 175.105, Primary Skin Irritant 16 CFR 1500.41, Primary Eye Irritant 16 CFR 1500.42

LINER DESCRIPTION: 44# PK

A polycoated brown kraft liner with superior die-cutting and stripping properties. Designed for high-speed label dispensing and is recommended for roll-to-roll applications.

Basis Weight (25 x 38 / 500), lbs.	48# +/- 10%
Caliper, mils	3.2 +/- 10%
Regulatory Compliances	CONEG, RoHS, REACH

All product specifications are for informational use only. Each customer and/or end user should determine the suitability of any product for their particular application. The above specifications are based on typical values and most current information. Specific products listed were current at the time of publication, however, all raw materials are subject to change.

Shelf Life: One year when stored at 72°F / 50% RH.