



Wausau Coated Products, Inc.

Product Specification WCD-0049

60# High Gloss Optimized For HP Indigo

Presses / Permanent Blockout / 80# Score Back

Sheet Size 12" x 18"

FACESTOCK DESCRIPTION: 60# Semi Gloss Optimized For HP Indigo Presses

High quality, high brightness, highly opaque, semi gloss facestock with excellent gloss level. Top coated and optimized for HP Indigo Presses. Base sheet contains archival properties, is elemental chlorine free and lignin free. It features excellent ink anchorage and high strength for die cutting and matrix stripping.

Basis Weight (25 x 38 / 500), lbs.	60
Caliper, mils	3
Brightness, %	90
Opacity, %	91
Tear, MD / CD, g	30 / 30
Tensile, MD / CD, lbs.	35 / 17
Regulatory Compliances	ASTM F963 Child Toy Safety, California Proposition 65, CONEG, RoHS

ADHESIVE DESCRIPTION: Permanent Opaque

A cold temperature emulsion acrylic permanent with a gray opaque feature. It exhibits good initial tack and good adhesion to a variety of substrates. Adhesion to rigid plastics, films, glass, and painted metals is good. Cuts and die-cuts cleanly. Good choice for sheet and roll-to-sheet applications.

Type	Cold Temperature Permanent
Classification	Emulsion Acrylic
pH	Alkaline
Minimum Application Temp., °F	35
Service Temperature Range, °F	-10 to +200
Regulatory Compliances	California Proposition 65, CONEG

LINER DESCRIPTION: 80# Score Back

Clay-coated bleached kraft liner designed for roll-to-sheet applications. Manufactured with liner scores every 1-1/4" apart.

Basis Weight (25 x 38 / 500), lbs	84.5
Caliper, mils	4.6
Opacity, %	86
Tear, MD / CD, g	61 / 71
Tensile, MD / CD, psi	36 / 21
Regulatory Compliances	Acid Free, ASTM F963 Child Toy Safety, California Proposition 65, CONEG, RoHS, REACH, FDA 21 CFR 175.105

All product specifications are for informational use only. Each customer and/or end user should determine the suitability of any product for their particular application. The above specifications are based on typical values and most current information. Specific products listed were current at the time of publication, however, all raw materials are subject to change.

Shelf Life: One year when stored at 72°F / 50% RH.