



**FACESTOCK DESCRIPTION: 2.6 mil Gold Inkjet Polyester**

A smooth gold film with a metallic finish engineered for inkjet printers and full process color printing. It is top coated to allow water-based inks to dry quickly and provide exceptional print quality. This label material is water and abrasion resistant.

Caliper, mils	2.6
Yield, sq in/lb	20,999
Elongation @ Break, MD / TD, %	115 / 92
Tensile Strength at Break, MD / TD, psi	28,000 / 34,000

Avoid exposure to ozone, exhaust fumes or solvent vapors as the absorptive nature of the print receptive topcoat could result in discoloration.

**ADHESIVE DESCRIPTION: i8017**

i8017 is an ultra-aggressive permanent designed for difficult-to-label surfaces. It offers excellent initial tack and ultimate adhesion to a variety of substrates. i8017 is UV resistant, water resistant, and offers some solvent resistance.

Type	High Performance Acrylic
Classification	Acrylic
pH	Slightly Acidic
Minimum Application Temp., °F	+20
Service Temperature Range, °F	-20 to +300
Regulatory Compliances	California Proposition 65, CONEG, Natural Rubber Latex Free, REACH, RoHS, FDA 21 CFR 175.105, FDA 21 CFR 175.125 Table 2 D-G, FDA 21 CFR 176.180

**LINER DESCRIPTION: 50# SC**

A supercalendered bleached kraft liner. Superior die-cutting and stripping properties. Recommended for roll-to-sheet or roll-to-fanfold applications. Good back printability.

Basis Weight (25 x 38 / 500), lbs.	57.5
Caliper, mils	3.2
Brightness, %	78
Gloss, 75°, %	48
Opacity, %	75
Tear, MD / CD, g	44 / 48
Tensile, MD / CD, lbs.	43 / 27
Regulatory Compliances	ASTM F963 Child Toy Safety, CONEG, RoHS, REACH, Lignin Free

All product specifications are for informational use only. Each customer and/or end user should determine the suitability of any product for their particular application. The above specifications are based on typical values and most current information. Specific products listed were current at the time of publication, however, all raw materials are subject to change.

Shelf Life: One year when stored at 72°F / 50% RH.