



FACESTOCK DESCRIPTION: 50# Premium Uncoated Laser / Inkjet

Premium quality uncoated paper with high brightness and an extremely smooth surface technologically engineered for inkjet and laser printers as well as color copiers. Also suitable for flexographic and offset printing.

| | |
|------------------------------------|---|
| Basis Weight (25 x 38 / 500), lbs. | 50 |
| Caliper, mils | 3.5 |
| Brightness, % | 94 |
| Opacity, % | 88 |
| Tear, MD / CD, g | 40 / 40 |
| Tensile, MD / CD, lbs. | 25 / 17 |
| Smoothness, Sheffield, units | 90 |
| pH | Alkaline |
| Regulatory Compliances | ASTM F963 Child Toy Safety, California Proposition 65, CONEG, RoHS, REACH |

ADHESIVE DESCRIPTION: PCT-241

Cold temperature emulsion acrylic permanent which exhibits high initial tack and very good adhesion to a variety of substrates including corrugated, rigid plastics, films, glass, and painted metal substrates. It offers good die-cutting and stripping characteristics. It is not recommended for water immersion.

| | |
|-------------------------------|---|
| Type | Cold Temperature Permanent |
| Classification | Emulsion Acrylic |
| pH | Alkaline |
| Minimum Application Temp., °F | 25 |
| Service Temperature Range, °F | -10 to +200 |
| Regulatory Compliances | ASTM F963 Child Toy Safety, CONEG, RoHS, Acute Oral Toxicity 16 CFR 1500.3, REACH, Non-ozone Depleting, FDA 21 CFR 175.105, Primary Skin Irritant 16 CFR 1500.41, Primary Eye Irritant 16 CFR 1500.42 |

LINER DESCRIPTION: 40# SC

A supercalendered bleached liner. Superior die-cutting and stripping properties. Recommended for roll-to-roll applications. Good back printability.

| | |
|------------------------------------|-----|
| Basis Weight (25 x 38 / 500), lbs. | 42 |
| Caliper, mils | 2.5 |

All product specifications are for informational use only. Each customer and/or end user should determine the suitability of any product for their particular application. The above specifications are based on typical values and most current information. Specific products listed were current at the time of publication, however, all raw materials are subject to change.

Shelf Life: One year when stored at 72°F / 50% RH.