



Wausau Coated Products, Inc.

Product Specification W012036

63# Silver Metalized Paper Optimized

for HP Indigo Presses / PCT-245 / 40# SC

FACESTOCK DESCRIPTION: 63# Silver Metalized Paper Optimized For HP Indigo Presses

A smooth bright silver metalized paper with the appearance of foil. Has superior converting properties and is top coated and optimized for HP Indigo Presses.

| | |
|------------------------------------|--|
| Basis Weight (25 x 38 / 500), lbs. | 63 |
| Caliper, mils | 3.2 |
| Tear, MD / CD, g | 48 / 48 |
| Tensile, MD / CD, lbs. | 34 / 20 |
| Stiffness, (Gurley), MD/ CD, mg | 141 / 95 |
| Regulatory Compliances | ASTM F963 Child Toy Safety, California Proposition 65, CONEG, CPSIA, Non-ozone Depleting |

ADHESIVE DESCRIPTION: PCT-245

A cold temperature emulsion acrylic permanent which exhibits good initial tack and good adhesion to a variety of substrates including corrugated, rigid plastics, films, glass, and painted metal surfaces. It offers excellent die-cutting and stripping characteristics. Adhesive designed for face and back label use on glass bottles and remains affixed when immersed in an ice bucket. It also features short term repositionability on bottles and hot water removability depending on face, substrate, wate

| | |
|-------------------------------|--|
| Type | Cold Temperature Permanent |
| Classification | Emulsion Acrylic |
| pH | Alkaline |
| Minimum Application Temp., °F | 25 |
| Service Temperature Range, °F | -10 to +200 |
| Regulatory Compliances | ASTM F963 Child Toy Safety, CONEG, RoHS, Acute Oral Toxicity 16 CFR 1500.3, REACH, FDA 21 CFR 175.105, Primary Skin Irritant 16 CFR 1500.41, Primary Eye Irritant 16 CFR 1500.42 |

LINER DESCRIPTION: 40# SC

A supercalendered bleached liner. Superior die-cutting and stripping properties. Recommended for roll-to-roll applications. Good back printability.

| | |
|------------------------------------|-----|
| Basis Weight (25 x 38 / 500), lbs. | 42 |
| Caliper, mils | 2.5 |

All product specifications are for informational use only. Each customer and/or end user should determine the suitability of any product for their particular application . The above specifications are based on typical values and most current information. Specific products listed were current at the time of publication, however, all raw materials are subject to change.

Shelf Life: One year when stored at 72°F / 50% RH.