



Wausau Coated Products, Inc.

Product Specification W019134

60# Top Coated Semi Gloss Optimized

for UV Inkjet Presses / PCT-241 / 40# SC

FACESTOCK DESCRIPTION: 60# Top Coated Semi Gloss Optimized for UV Inkjet Presses

High quality, high brightness, highly opaque, semi gloss facestock. Top coated and optimized for UV Inkjet Presses. The base sheet is elemental chlorine free and lignin free. It features high strength for die cutting and matrix stripping.

Basis Weight (25 x 38 / 500), lbs.	60
Caliper, mils	3
Brightness, %	90
Opacity, %	91
Tear, MD / CD, g	30 / 30
Tensile, MD / CD, lbs.	35 / 17

Avoid exposure to ozone, exhaust fumes or solvent vapors as the absorptive nature of the print receptive topcoat could result in discoloration.

ADHESIVE DESCRIPTION: PCT-241

Cold temperature emulsion acrylic permanent which exhibits high initial tack and very good adhesion to a variety of substrates including corrugated, rigid plastics, films, glass, and painted metal substrates. It offers good die-cutting and stripping characteristics. It is not recommended for water immersion.

Type	Cold Temperature Permanent
Classification	Emulsion Acrylic
pH	Alkaline
Minimum Application Temp., °F	25
Service Temperature Range, °F	-10 to +200
Regulatory Compliances	ASTM F963 Child Toy Safety, CONEG, RoHS, Acute Oral Toxicity 16 CFR 1500.3, REACH, Non-ozone Depleting, FDA 21 CFR 175.105, Primary Skin Irritant 16 CFR 1500.41, Primary Eye Irritant 16 CFR 1500.42

LINER DESCRIPTION: 40# SC

A supercalendered bleached liner. Superior die-cutting and stripping properties. Recommended for roll-to-roll applications. Good back printability.

Basis Weight (25 x 38 / 500), lbs.	42
Caliper, mils	2.5

All product specifications are for informational use only. Each customer and/or end user should determine the suitability of any product for their particular application. The above specifications are based on typical values and most current information. Specific products listed were current at the time of publication, however, all raw materials are subject to change.

Shelf Life: One year when stored at 72°F / 50% RH.